



PRODUCT DATA SHEET

Product	Oil Well Cement
Standard	Equivalent to API Spec 10A Type "G" HSR

Producer	AS Çimento Sanayi ve Ticaret Anonim Şirketi İçeriovaalan Mevkii, 15310 Bucak, Burdur, Turkey Tel : +90 248 331 30 00 Fax : +90 248 331 22 22 info@ascimento.com.tr
-----------------	---

Product Description	This product is basic oil well cement that generally uses for primary cementing of middle depth oil wells. Contains sulphate resistance cement clinkler and natural gypsum only.
----------------------------	--

Vessel	:
Port of discharge	:
Company	:
Shipper	:
Tonnage	:
Date of loading	:
Date of B/L	:

Chemical Properties (*)	As Cement Declaration	Standard	Unit
SO ₃	2,7	max. 3,0	%
MgO	1,0	max. 6,0	%
Loss On Ignition	1,9	max. 3,0	%
Insoluble Residue	0,40	max. 0,75	%
C3S	60	between 48 - 65	%
C3A	2,50	max. 3,0	%
C4AF + 2C3A	20,15	max. 24,0	%
Alkali Equivalent	0,61	max. 0,75	%

Physical Properties (*)	As Cement Declaration	Standard	Unit
Free Fluid Content	4,50	max. 5,9	%
Specific Gravity	3,19		g/cm ³
Compressive Strength at 140 F at 8 hours	2000	min. 1500	psi
Max. Consistency 0-30 minutes stirring period	25,0	max. 30	BC
Thickening time at 5160 psi & 52 C raised 28 min	105,0	between 90 - 120	minutes

Delivery Type	Sold in bulk or in 50 kg. Kraft bags or 1,5 MT Big-Bags
----------------------	---

Quality Control System	Our factory has ISO 9001:2000 Certificate.
-------------------------------	--

For More Information	quality@ascimento.com.tr sales@ascimento.com.tr	For Technical For Commercial
-----------------------------	--	---------------------------------

(*) These data represent the average values of 2010 of this product till the 07 April 2010

